## Heatshrink & Repair | HEATSHRINK END CAPS & REPAIR

HEATSHRINK CABLE END CAPS

## End Caps Heatshrink Cable End Caps

Remora Heatshrink end caps are manufactured from cross-linked polyolefin material and are coated with a hot melt adhesive on the inner surface. This provides a water tight seal against the damage of moisture, dirt or corrosion. The rugged wall of these end caps also offers excellent resistance against abrasion. Suitable for use on polymeric and paper insulated, lead jacketed cables.

Internal Diameter



## **Heatshrink Cable End Caps**

- Good chemical resistance
- · Good solvent resistance
- Unaffected by UV light
- 2:1 Shrink Ratio
- Zero Halogen

Dielectric Strength: 12 kV/mm min Temperature Range: -55°C to 100°C Shrink Temperature: +120°C Tensile Strength: 12.0 MPa min

Tensile Strength After Heat Ageing: 168 hours @ 150°C - 12 MPa min

Elongation: 200% min

Elongation After Heat Ageing: 168 hours @ 150°C - 200% min Material: Cross-linked Polymeric. Internally Coated with Hot Melt Adhesive

Material: External Thermochromic Paint

Shelf-Life: 5 years minimum when stored: -10°C to +40°C <75% rel. humidity

Colour: Black



Shrunk

Code	Max Before Shrink	Min After Shrink	Wall Thickness	Length	
HSEC12	12.0	4.0	2.6	40.0	
HSEC20	20.0	6.0	2.2	42.0	
HSEC25	25.0	8.5	2.5	65.0	
HSEC40	40.0	15.0	3.3	75.0	
HSEC55	55.0	25.0	3.3	107.0	
HSEC75	75.0	35.0	3.3	127.0	
HSEC100	100.0	50.0	4.0	152.0	
HSEC120	120.0	60.0	4.0	152.0	
HSEC148	148.0	57.0	4.0	152.0	
HSEC160	160.0	82.0	4.0	152.0	



Wiring Terminals

Tooling

Earthing Lightning

Jointing

shrink

Clea

Ties

MICC Cable

onduit

Fixing & Security